



Wave 3 and Wave 5 Datasheet

Wave3 , Ø65 mm Light (Cr39) $n=1,498$, $abbe=58$, $\gamma=1,19$

Nominal Base	Radius Convex (mm)	True Base	Thickness edge (mm)	Center Thickness (mm)	Optic field (mm)
10	51,00	9,76	8,0	9,5	41
12	43,30	11,50	8,0	11,0	40
14	36,70	13,57	8,0	11,5	39
16	33,80	14,73	8,0	12,5	37
18	29,00	17,17	8,0	13,2	36
20	27,87	17,86	8,0	17,0	34
23	24,66	20,19	8,0	17,0	32
27	21,15	23,54	8,0	18,5	30

Wave3 semi finished , Ø65 MR8 (High Index) $n=1,597$, $abbe=41$, $\gamma=1,30$

Nominal Base	Radius Convex (mm)	True Base	Thickness edge (mm)	Center Thickness (mm)	Optic field (mm)
10	51,00	11,70	8,0	9,5	41
12	43,30	13,78	8,0	11,0	40
14	36,70	16,26	8,0	11,5	39
16	33,10	18,03	8,0	12,5	37
18	29,10	20,51	8,0	13,2	36
20	27,87	21,42	8,0	17,0	34
23	24,66	24,21	8,0	17,0	32
27	21,15	28,23	8,0	18,5	30



Light (Cr39) $n=1,498$, $abbe=58$, $\gamma=1,19$

Nominal Base	Radius Convex (mm)	True Base	Thickness edge (mm)	Center Thickness (mm)	Optic field (mm)
10	54,04	9,22	8,0	11,0	40
12	43,31	11,50	8,0	14,1	40
14	36,50	13,64	8,0	14,8	40
16	31,25	15,94	8,0	16,7	40
18	27,66	18,00	8,0	16,9	40
20	24,72	20,14	8,0	17,2	38
22	22,40	22,23	8,0	17,8	38